

PRODUCT DATA SHEET

Revision Date: 13/01

ATUREX® 365LC

Modified Cycloaliphatic Amine Adduct

It is accelerated version of ATUREX 340 offering faster cure rate and hardness development.

FEATURES

- Cure at low temperatures under damp conditions
- Good film properties
- Excellent color and color stability
- Good adhesion and very good chemical resistance

- Good water resistance
- Range of cure times and pot lives
- Very good heat-cure performance

APPLICATIONS

- Solvent-free and high-solids coatings
- Adhesives
- Grouts and lamination
- Mortars

PROPERTIES	TYPICAL QUALITY	SPECIFICATION
Specific Gravity, 25°C	1.05	1.05
Solids, %	-	-
AHEW	93	93
Use Level, phr	50	50
Gel Time, min/150g, 25°C	30	30
Thin Film Set Time, hr/25°C	5.5	5.5
Typical Cure Schedule	4 days	2-7 days at ambient
TYPICAL PROPERTIES		
Amine Value, mg KOH/g	360	345-375
Viscosity, mPa.s, 25°C	500	300-700
Color, Gardner	1	<2
HANDLING & STORAGE	In unopened, original containers at 2 - 40° C, (see Expiry date on original container)	
CN CODE	3908900000	
PACKAGING	In 210 liter tight head steel drums, net weight 190kg.	
HEALTH & SAFETY	Please refer to Material Safety Data Sheet	



Economic Development Zone, Yichun, Jiangxi, China.
Phone: +86 186 0795 0576 Tel: +86 795 3586166
Fax: +86 795 3586165 E-Mail: jackie@aturex.com
Web: www.aturex.com