Revision Date: 13/01

ATUREX® 495

Ketimine Polyamide Amine

Good water resistance

adverse conditions

better cure under

Ketimine ATUREX 450-type polyamide is for thin film applications.

FEATURES

 Good compatibility (without Induction period)

APPLICATIONS

- Cationic electro-deposition
- coatings
- One-component epoxy composites

PROPERTIES	TYPICAL QUALITY	SPECIFICATION
Specific Gravity, 25° C	0.98	0.98
Solids, %	-	-
AHEW	-	-
Use Level, phr	-	-
Gel Time, min/150g, 25° C	-	-
Thin Film Set Time, hr/25° C	Solid Resin	2.0
Typical Cure Schedule	4 days	2-7 days at ambient
TYPICAL PROPERTIES		
Amine Value, mg KOH/g	246	240-260
Viscosity, mPa.s, 25° C	22000	15000-30000
Color, Gardner	8	<12
HANDLING & STORAGE	In unopened, original containers at 2 - 40° C, (see Expiry date on original container)	
CN CODE	3908900000	
PACKAGING	In 210 liter tight head steel drums, net weight 190kg.	
HEALTH & SAFETY	Please refer to Material Safety Data Sheet	



Economic Development Zone, Yichun, Jiangxi, China. Phone: +86 186 0795 0576 Tel: +86 795 3586166 Fax: +86 795 3586165 E-Mail: jackie@aturex.com

Web: www.aturex.com