

PRODUCT DATA SHEET

Revision Date: 13/01

ATUREX® 525W60

Polyamide Amine Adduct

Equivalent performance and lower viscosity compared to ATUREX 540W60. It is low cost-in-use.

FEATURES

- Good abrasion resistance
- Zero-VOC achievable
- Low viscosity and color
- Low odor and non-flammable
- Easy to clean-up and apply.
- Good adhesion

APPLICATIONS

- Waterborne coatings.
- Primers and sealers for floors
- Walls and other concrete structures.
- Civil engineering, marine and general industrial areas

| PROPERTIES | TYPICAL QUALITY | SPECIFICATION |
|------------------------------|--|---------------------|
| Specific Gravity, 25° C | 1.08 | 1.08 |
| Solids, % | 60 | 58-62- |
| AHEW | 200 | 200 |
| Use Level, phr | 105 | 105 |
| Gel Time, min/150g, 25° C | 60 | 60 |
| Thin Film Set Time, hr/25° C | 4.0 | 4.0 |
| Typical Cure Schedule | 4 days | 2-7 days at ambient |
| TYPICAL PROPERTIES | | |
| Amine Value, mg KOH/g | 250 | 230-270 |
| Viscosity, mPa.s, 25° C | 8000 | 4000-12000 |
| Color, Gardner | 8 | <12 |
| HANDLING & STORAGE | In unopened, original containers at 2 - 40° C, (see Expiry date on original container) | |
| CN CODE | 3908900000 | |
| PACKAGING | In 210 liter tight head steel drums, net weight 190kg. | |
| HEALTH & SAFETY | Please refer to Material Safety Data Sheet | |



Economic Development Zone, Yichun, Jiangxi, China.
Phone: +86 186 0795 0576 Tel: +86 795 3586166
Fax: +86 795 3586165 E-Mail: jackie@aturex.com
Web: www.aturex.com

Publication number 10086 – Revision Jan.2013

The information and statements herein are believed to be reliable, but not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification.