

PRODUCT DATA SHEET

Revision Date: 13/01

ATUREX® 620BC70

Ketimine Polyamide Amine

It is 70% solution of ketimine semi-solid polyamide in BCS for thick film applications.

FEATURES

- Good compatibility (without induction period)
- Good water resistance
- better cure under adverse conditions

APPLICATIONS

- Cationic electro-deposition coatings
- One-component epoxy composites

PROPERTIES	TYPICAL QUALITY	SPECIFICATION
Specific Gravity, 25°C	0.95	0.95
Solids, %	70	68-72
AHEW	-	-
Use Level, phr	-	-
Gel Time, min/150g, 25°C	-	-
Thin Film Set Time, hr/25°C	-	-
Typical Cure Schedule	4 days	2-7 days at ambient
TYPICAL PROPERTIES		
Amine Value, mg KOH/g	63	60-70
Viscosity, mPa.s, 25°C	10000	9500-12500
Color, Gardner	8	<12
HANDLING & STORAGE	In unopened, original containers at 2 - 40°C, (see Expiry date on original container)	
CN CODE	3089000000	
PACKAGING	In 210 liter tight head steel drums, net weight 190kg.	
HEALTH & SAFETY	Please refer to Material Safety Data Sheet	



Economic Development Zone, Yichun, Jiangxi, China.
Phone: +86 186 0795 0576 Tel: +86 795 3586166
Fax: +86 795 3586165 E-Mail: jackie@aturex.com
Web: www.aturex.com