# **PRODUCT DATA SHEET**

Revision Date: 13/01

# ATUREX® 630

### **Alcohol-soluble and General Polyamide Resin**

ATUREX 630 the alcohol-soluble polyamide resin is easily dissolute in alcohol. It can be dissolute in 95% dehydrated alcohol, dissolves aids the release is extremely good, It widely used in the domain such as gravure printing ink of plastic film, the flexor printing ink of plastic film domain.

#### **FEATURES**

- Good stability
- Solvent release good
- Low temperaturedoes not gel
- Excellent gloss and adhesion

### **APPLICATIONS**

- Gravure printing ink
- Paper thin film printing ink
- Primer coatings
- Over-printing varnish

PROPERTIES	Spec.	TEST METHOD	ANALYSIS RESULT	
Aspect	Visual	Visual	Light yellow granular	
Amine Number, mg KOH/g	<6	ISO9702	2.4	
Color, Gardner	<10	ISO4630	5+	
Viscosity, mPa.s, 40°C	90-150	ISO3219	140	
TYPICAL PROPERTIES				
Softening Point °C	120+5		121	
Acid Value (mgKOH/g)	<5		1.8	
Freezing point °C	>7		3	
HANDLING & STORAGE		In unopened, original containers, several years at 2 - 40°C, (see Expiry date on original container)		
BATCH NUMBER	3908900000	3908900000		
QUANTITY	2000KG	2000KG		
PACKAGING	Paper and plastic	Paper and plastic bags, net weight 25kg.		
HEALTH & SAFETY	Please refer to M	Please refer to Material Safety Data Sheet		



Economic Development Zone, Yichun, Jiangxi, China. Tel: +86 795 3586166 Fax: +86 795 3586165 E-Mail: jackie@aturex.com Web: www.aturex.com